


SPECIFICATION SHEET

# KFR-DOPO



Chemical Name:	9,10-dihydro-9-oxa-10-phosphaphenanthrene-10-oxide
CAS No.:	35948-25-5
Appearance:	White flake
Assay(%)	99% min.
Melting Point.:	116°C~ 119°C
Boiling Point:	200°C/1mm Hg
Specific gravity:	1.378/25°C
Transmittance: (1g in 10mL methanol)	T425nm ≥98%
Solubility:	Easily soluble in methanol, ethanol, isopropanol, chloroform, DMF, DMSO. Slightly soluble in benzene, toluene. Hardly soluble in water, n-hexane.

**KUO CHING CHEMICAL COMPANY, LIMITED**

Head Office:  
5F, No.229, Chung Shing Street,  
Taichung, Taiwan  
Tel:886-4-2321-5616  
Fax:886-4-2310-9292

Chung Li Plant:  
No.35-5 19th Lin, Tong Shin Li  
Ping Chen City  
Taoyuan County, Taiwan  
Tel:886-3-450-1643

Nangtou Plant:  
No.16 Industrial North Road  
Nangtou, Taiwan  
Tel:886-49-2259-946

Taichung Plant:  
No.12 18th Industrial Road  
Taichung, Industrial Park  
Taichung, Taiwan  
Tel:886-4-2350-7102

**Chemical properties:** Although this product easily absorb the moisture in the open air caused influent the quality situation but it is restored by heating again.

**Application:** Flame retardant epoxy resin for PCB: Owing to the rigid structure of KFR-DOPO and pendant phosphorus group, the resultant phosphorus containing epoxy resin exhibited better environmentally retardant, higher glass transition temperature, thermal stability, less toxic and smoke than the conventional flame retardant epoxy resin systems containing tetrabromo bisphenol A(TBBA). UL94-VO rating could be achieved with a phosphorus content of 2% in epoxy resin. It has demonstrated superior ability as flame retardant for printed circuit board (PCB) and electrical laminate.

---

**KUO CHING CHEMICAL COMPANY, LIMITED**

Head Office:  
5F, No.229, Chung Shing Street,  
Taichung, Taiwan  
Tel:886-4-2321-5616  
Fax:886-4-2310-9292

Chung Li Plant:  
No.35-5 19th Lin, Tong Shin Li  
Ping Chen City  
Taoyuan County, Taiwan  
Tel:886-3-450-1643

Nangtou Plant:  
No.16 Industrial North Road  
Nangtou, Taiwan  
Tel:886-49-2259-946

Taichung Plant:  
No.12 18th Industrial Road  
Taichung, Industrial Park  
Taichung, Taiwan  
Tel:886-4-2350-7102